

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C25C 3/12, 7/02	A1	(11) International Publication Number: WO 99/36594 (43) International Publication Date: 22 July 1999 (22.07.99)												
(21) International Application Number: PCT/IB99/00084 (22) International Filing Date: 19 January 1999 (19.01.99) (30) Priority Data: <table border="0"><tr><td>PCT/IB98/00080</td><td>20 January 1998 (20.01.98)</td><td>IB</td></tr><tr><td>09/126,206</td><td>30 July 1998 (30.07.98)</td><td>US</td></tr><tr><td>09/126,840</td><td>30 July 1998 (30.07.98)</td><td>US</td></tr><tr><td>09/126,359</td><td>30 July 1998 (30.07.98)</td><td>US</td></tr></table> (71) Applicant (for all designated States except US): MOLTECH INVENT S.A. [LU/LU]; 68-70, boulevard de la Pétrusse, L-2320 Luxembourg (LU). (72) Inventors; and (75) Inventors/Applicants (for US only): DE NORA, Vittorio [IT/BS]; Sandrigham House, Nassau (BS). DURUZ, Jean-Jacques [CH/CH]; Rue de Hesse 4, CH-1204 Geneva (CH). (74) Agent: CRONIN, Brian; Moltech S.A., Route de Troinex 9, CH-1227 Carouge (CH).		PCT/IB98/00080	20 January 1998 (20.01.98)	IB	09/126,206	30 July 1998 (30.07.98)	US	09/126,840	30 July 1998 (30.07.98)	US	09/126,359	30 July 1998 (30.07.98)	US	(81) Designated States: AT, AU, BR, CA, CH, CN, CZ, DE, DK, ES, GB, GH, HU, ID, IN, IS, JP, KP, KR, MX, NO, NZ, PL, RO, RU, SE, SI, SK, TJ, TR, UA, US, YU, ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
PCT/IB98/00080	20 January 1998 (20.01.98)	IB												
09/126,206	30 July 1998 (30.07.98)	US												
09/126,840	30 July 1998 (30.07.98)	US												
09/126,359	30 July 1998 (30.07.98)	US												
(54) Title: NON-CARBON METAL-BASED ANODES FOR ALUMINIUM PRODUCTION CELLS (57) Abstract A non-carbon metal-based anode of a cell for the electrowinning of aluminium comprising an electrically conductive metal substrate resistant to high temperature, the surface of which becomes passive and substantially inert to the electrolyte, and a coating adherent to the metal substrate making the surface of the anode electrochemically active for the oxidation of oxygen ions present at the electrolyte interface. The substrate metal may be selected from nickel, cobalt, chromium, molybdenum, tantalum and the Lanthanide series. The active constituents of the coating are for example oxides such as spinels or perovskites, oxyfluorides, phosphides or carbides, in particular ferrites. The active constituents may be coated onto the substrate from a slurry or suspension containing colloidal material and the electrochemically active material.														

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon			PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

- 1 -

NON-CARBON METAL-BASED ANODES FOR
ALUMINIUM PRODUCTION CELLS

Field of the Invention

This invention relates to non-carbon metal-based anodes for use in cells for the electrowinning of aluminium by the electrolysis of alumina dissolved in a molten fluoride-containing electrolyte, and to methods for their fabrication and reconditioning, as well as to electrowinning cells containing such anodes and their use to produce aluminium.

Background Art

10 The technology for the production of aluminium by the electrolysis of alumina, dissolved in molten cryolite containing salts, at temperatures around 950°C is more than one hundred years old.

15 This process, conceived almost simultaneously by Hall and Héroult, has not evolved as many other electrochemical processes.

20 The anodes are still made of carbonaceous material and must be replaced every few weeks. The operating temperature is still not less than 950°C in order to have a sufficiently high solubility and rate of dissolution of alumina and high electrical conductivity of the bath.

25 The anodes have a very short life because during electrolysis the oxygen which should evolve on the anode surface combines with the carbon to form polluting CO₂ and small amounts of CO and fluoride-containing dangerous gases. The actual consumption of the anode is as much as

- 2 -

450 Kg/Ton of aluminium produced which is more than 1/3 higher than the theoretical amount of 333 Kg/Ton

The frequent substitution of the anodes in the cells is still a clumsy and unpleasant operation. This cannot be avoided or greatly improved due to the size and weight of the anode and the high temperature of operation.

Several improvements were made in order to increase the lifetime of the anodes of aluminium electrowinning cells, usually by improving their resistance to chemical attacks by the cell environment and air to those parts of the anodes which remain outside the bath. However, most attempts to increase the chemical resistance of anodes were coupled with a degradation of their electrical conductivity.

US Patent 4,614,569 (Duruz/Derivaz/Debely/Adorian) describes non-carbon anodes for aluminium electrowinning coated with a protective coating of cerium oxyfluoride, formed in-situ in the cell or pre-applied, this coating being maintained by the addition of cerium compounds to the molten cryolite electrolyte. This made it possible to have a protection of the surface only from the electrolyte attack and to a certain extent from the gaseous oxygen but not from the nascent monoatomic oxygen.

EP Patent application 0 306 100 (Nyguen/Lazouni/Doan) describes anodes composed of a chromium, nickel, cobalt and/or iron based substrate covered with an oxygen barrier layer and a ceramic coating of nickel, copper and/or manganese oxide which may be further covered with an in-situ formed protective cerium oxyfluoride layer.

Likewise, US Patents 5,069,771, 4,960,494 and 4,956,068 (all Nyguen/Lazouni/Doan) disclose aluminium production anodes with an oxidized copper-nickel surface

- 3 -

on an alloy substrate with a protective barrier layer. However, full protection of the alloy substrate was difficult to achieve.

A significant improvement was described in US Patent 5,510,008, and in International Application WO96/12833 (Sekhar/Liu/Duruz) involved a anode having a micropyroretically produced body from a combination of nickel, aluminium, iron and copper and oxidising the surface before use or in-situ during electrolysis. By said micropyroretic methods materials have been obtained whose surfaces when oxidised are active for the anodic reaction and whose metallic interior has low electrical resistivity to carry a current from high electrical resistant surface to the busbars. However it would be useful, if it were possible, to simplify the manufacturing process of these materials obtained from powders and increase their life to make their use economic.

Metal or metal based anodes are highly desirable in aluminium electrowinning cells instead of carbon-based anodes. Many attempts were made to use metal-based anodes for aluminium production, however they were never adopted by the aluminium industry because of their poor performance.

Objects of the Invention

An object of the invention is to substantially reduce the consumption of the active anode surface of an aluminium electrowinning anode which is attacked by the nascent oxygen by enhancing the reaction of nascent oxygen to biatomic molecular gaseous oxygen.

Another object of the invention is to provide a coating for an aluminium electrowinning anode which has a high electrochemical activity and also a long life and

- 4 -

which can be replaced as soon as such activity decreases or when the coating is worn out.

A major object of the invention is to provide an aluminium electrowinning anode which has no carbon so as to eliminate carbon-generated pollution and reduce the cost of operation.

Summary of the Invention

The invention provides a non-carbon metal-based anode of a cell for the electrowinning of aluminium, in particular by the electrolysis of alumina dissolved in a molten fluoride-containing electrolyte. The anode comprises an electrically conductive metal substrate resistant to high temperature, the surface of which becomes passive and substantially inert to the electrolyte, and an electrochemically active coating adherent to the surface of the metal substrate making and keeping the surface of the anode conductive and electrochemically active for the oxidation of oxygen ions present at the electrolyte interface.

Whereas conventional coatings are usually used to protect a conductive substrate of a cell component from chemical and/or mechanical attacks destroying the substrate, this particular treatment is applied in the form of a coating onto a passivable substrate to maintain the anode surface conductive and electrochemically active and protect it from electrolyte attack wherever the coating covers the surface even though the coating may be imperfect or incomplete.

This allows the coated surfaces of the anode to remain electrochemically active during electrolysis, while the remaining parts of the surface of the metal substrate become inert to the electrolyte. This passivation property offers a self-healing effect, i.e. when the surface of the anode is imperfectly covered,

- 5 -

damaged or partly worn out, parts of the metal substrate which come into contact with the electrolyte are automatically passivated during electrolysis and become inert to the electrolyte and not corroded.

5 Metal substrates providing for this self-healing effect in molten fluoride-based electrolyte may be made of one or more metals selected from nickel, cobalt, chromium, molybdenum, tantalum and the Lanthanide series of the Periodic Table, and their alloys or
10 intermetallics, such as nickel-plated copper.

The coatings usually comprise:

- a) at least one electrically conductive and electrochemically active constituent,
- b) an electrocatalyst, and
- 15 c) a bonding material substantially resistant to cryolite and oxygen for bonding these constituents together and onto the passivable metal substrate.

These constituents are usually co-applied though it is possible to provide sequential application of the
20 different constituents.

The presence of one or more electrocatalysts is desirable, although not essential for the invention. Likewise the presence of bonding material is not always necessary.

25 Coatings can be obtained by applying their active constituents and their precursors by various methods which can be different for each constituent and can be repeated in several layers. For example, a coating can be obtained by directly applying a powder onto the
30 passivable metal substrate or constituents of the coating may be applied from a slurry or suspension containing colloidal or polymeric material. The colloidal

- 6 -

material can be a binder solely or can be part of the active material. The colloidal material may include at least one colloid selected from colloidal alumina, ceria, lithia, magnesia, silica, thoria, yttria, zirconia, tin
5 oxide, zinc oxide and colloid containing the active material.

When a slurry or a suspension containing colloidal material is applied the dry colloid content corresponds to up to 50 weight% of the colloid plus liquid carrier,
10 usually from 10 to 20 weight%.

The coating can be applied on the substrate by plasma spraying, physical vapor deposition (PVD), chemical vapor deposition (CVD), electrodeposition or callendering rollers. A slurry or a dispersion is
15 preferably applied by rollers, brush or spraying.

Usually the electrochemically active constituent(s) is/are selected from oxides, oxyfluorides, phosphides, carbides and combinations thereof.

The oxide may be present in the electrochemically
20 active layer as such, or in a multi-compound mixed oxide and/or in a solid solution of oxides. The oxide may be in the form of a simple, double and/or multiple oxide, and/or in the form of a stoichiometric or non-stoichiometric oxide.

The oxides may be in the form of spinels and/or perovskites, in particular spinels which are doped, non-stoichiometric and/or partially substituted. Doped spinels may comprise dopants selected from Ti^{4+} , Zr^{4+} , Sn^{4+} , Fe^{4+} , Hf^{4+} , Mn^{4+} , Fe^{3+} , Ni^{3+} , Co^{3+} , Mn^{3+} , Al^{3+} , Cr^{3+} ,
25 Fe^{2+} , Ni^{2+} , Co^{2+} , Mg^{2+} , Mn^{2+} , Cu^{2+} , Zn^{2+} and Li^{+} .
30

Such a spinel may be a ferrite, in particular a ferrite selected from cobalt, manganese, molybdenum, nickel and zinc, and mixtures thereof. The ferrite may be doped with at least one oxide selected from the group

- 7 -

consisting of chromium, titanium, tantalum, tin, zinc and zirconium oxide.

Nickel-ferrite or nickel-ferrite based constituents are advantageously used for their resistance to electrolyte and may be present as such or partially substituted with Fe^{2+} .

The coating may also contain a chromite which is usually selected from iron, cobalt, copper, manganese, beryllium, calcium, strontium, barium, magnesium, nickel and zinc chromite.

The electrochemically active constituents of the coating may be selected from iron, chromium, copper and nickel, and oxides, mixtures and compounds thereof, as well as a Lanthanide as an oxide or an oxyfluoride such as cerium oxyfluoride, and mixtures thereof.

When an electrocatalyst is present in the coating it is selected preferably from noble metals such as iridium, palladium, platinum, rhodium, ruthenium, or silicon, tin and zinc, the Lanthanide series of the Periodic Table and mischmetal oxides, and mixtures and compounds thereof.

Coatings can be formed with or without reaction at low or high temperature. A reaction can either take place among the constituents of the coating; or between the constituents of the coating and the passivable metal substrate. When no reaction takes place to form the coating the active constituents must already be present in the applied material, for example in a slurry or suspension applied onto the substrate.

In order to manufacture these anodes any electrically conductive and heat-resisting materials may be used. However, metals which do not offer the self-healing effect can only be used as metal cores which must be coated with a layer forming the passivable metal substrate having this self-healing effect particularly

when exposed to a fluoride-containing electrolyte, such as cryolite.

The metal core may comprise metals, alloys, intermetallics, cermets and conductive ceramics, such as
5 metals selected from copper, chromium, cobalt, iron, aluminium, hafnium, molybdenum, nickel, niobium, silicon, tantalum, titanium, tungsten, vanadium, yttrium and zirconium, and combinations and compounds thereof.

For instance, the core may be made of an alloy
10 comprising 10 to 30 weight% of chromium, 55 to 90 weight% of at least one of nickel, cobalt and/or iron and 0 to 15 weight% of at least one of aluminium, hafnium, molybdenum, niobium, silicon, tantalum, tungsten, vanadium, yttrium and zirconium.

15 The core may be covered with an oxygen barrier layer. This layer may be obtained by oxidising the surface of the core when it contains chromium and/or nickel or by applying a precursor of the oxygen barrier layer onto the core and heat treating. Usually, the
20 oxygen barrier layer comprises chromium oxide and/or black non-stoichiometric nickel oxide.

The oxygen barrier layer may be covered in turn with at least one protective layer consisting of copper or copper and at least one of nickel and cobalt, and/or (an)
25 oxide(s) thereof to protect the oxygen barrier layer by inhibiting its dissolution into the electrolyte. For instance, the oxygen barrier layer may be coated first with a nickel layer and then with a copper layer, heat treated for several hours in an inert atmosphere, such as
30 5 hours at 1000°C in argon, to interdiffuse the nickel and the copper layer, and upon heat treatment in an oxidising media, such as an air oxidation for 24 hours at 1000°C, the interdiffused and oxidised nickel-copper layer constitutes a good a protective layer.

- 9 -

The invention relates also to a method of manufacturing the described non-carbon metal-based anode. The method comprises coating a substrate of electrically conductive metal resistant to high temperature the surface of which during electrolysis becomes passive and substantially inert to the electrolyte with at least one layer containing electrochemically active constituents or precursors thereof and heat-treating the or each layer on the substrate to obtain a coating adherent to the metal substrate making the surface of the anode electrochemically active for the oxidation of oxygen ions present at the electrolyte interface.

The method of the invention can be applied for reconditioning the non-carbon metal-based anode when at least part of the active coating has been dissolved or rendered non-active or dissolved. The method comprises clearing the surface of the substrate before re-coating said surface with a coating adherent to the passivable metal substrate once again making the surface of the anode electrochemically active for the oxidation of oxygen ions.

Another aspect of the invention is a cell for the production of aluminium by the electrolysis of alumina dissolved in a fluoride-containing electrolyte, in particular a fluoride-based electrolyte or a cryolite-based electrolyte or cryolite, having non-carbon metal-based anodes comprising an electrically conductive passivable metal substrate and a conductive coating having an electrochemically active surface as described hereabove.

Preferably, the cell comprises at least one aluminium-wettable cathode. Even more preferably, the cell is in a drained configuration by having at least one drained cathode on which aluminium is produced and from which aluminium continuously drains.

The cell may be of monopolar, multi-monopolar or bipolar configuration. A bipolar cell may comprise the anodes as described above as a terminal anode or as the anode part of a bipolar electrode.

5 Preferably, the cell comprises means to improve the circulation of the electrolyte between the anodes and facing cathodes and/or means to facilitate dissolution of alumina in the electrolyte. Such means can for instance be provided by the geometry of the cell as described in co-pending application PCT/IB98/00161 (de Nora/Duruz) or 10 by periodically moving the anodes as described in co-pending application PCT/IB98/00162 (Duruz/Bellò).

The cell may be operated with the electrolyte at conventional temperatures, such as 950 to 970°C, or at
15 reduced temperatures as low as 750°C.

The invention also relates to the use of such an anode for the production of aluminium in a cell for the electrowinning of aluminium by the electrolysis of alumina dissolved in a fluoride-containing electrolyte, wherein oxygen ions in the electrolyte are oxidised and released as molecular oxygen by the electrochemically active anode coating.

The invention will now be described in the following examples.

25 Example 1

An non-carbon metal-based anode is prepared according to the invention by hot calendar rolling at 900°C of nickel ferrite particles having a particle size of 10-50 micron into a nickel metal sheet of 2 mm 30 thickness used as an electrically conductive substrate for the anode. The nickel ferrite particles are coated onto the nickel sheet in an amount of 500 g/m².

- 11 -

After coating, the anode was tested in an electrolytic cell using cryolite with 6 weight% alumina as an electrolyte and a carbon cathode covered with molten aluminium. The anode was polarised at 1 A/cm² for 93 hours and sustained this current density during the entire test, the cell voltage remaining comprised between 5.5 and 5.8 Volts.

At the end of the test, the anode was dimensionally unchanged and no sign of corrosion could be detected at the anode surface.

Example 2

A non-carbon metal-based anode according to the invention was obtained from a nickel substrate which was coated with a slurry with subsequent heat-treatment.

The slurry was made from a solution consisting of 10 ml of colloidal magnesia acting as a binder mixed with 20 g of nickel ferrite powder providing the electrochemically active constituents, as described in Example 1.

The slurry was then applied onto the substrate by means of a brush. 15 successive layers were applied onto the substrate. Each time a layer had been applied onto the substrate, the layer was cured on the substrate by a heat treatment at 500°C for 15 minutes before applying the next layer.

After coating the substrate with the 15 successive layers the anode had a final coating of 0.6 to 1.0 mm thick.

The anode was then tested in a laboratory scale cell for the electrowinning of aluminium. 10 minutes after immersing the anode into the electrolytic bath the anode was extracted from the cell. The parts of the anodes which were not protected by the coating had been

- 12 -

passivated under the effect of the current by the formation of an inert and adherent nickel oxide layer formed on the uncoated surfaces which could be observed by optical microscopy and scanning electron microscopy of
5 a cross section of the anode after test.

Example 3

Similarly to Example 2, a coating was applied onto a nickel substrate in 10 layers, except that 0.2 g of iridium powder acting as a catalyst were added to the
10 mixture of colloidal alumina with nickel-nickel ferrite.

Similar results were observed.

- 13 -

CLAIMS

1. A non-carbon metal-based anode of a cell for the electrowinning of aluminium, in particular by the electrolysis of alumina dissolved in a molten fluoride-containing electrolyte, comprising an electrically
5 conductive metal substrate resistant to high temperature, the surface of which becomes passive and substantially inert to the electrolyte, and an electrochemically active coating adherent to the surface of the metal substrate
10 making and keeping the surface of the anode conductive and electrochemically active for the oxidation of oxygen ions present at the electrolyte interface.
2. The anode of claim 1, wherein the passivable metal substrate comprises at least one metal selected from
15 nickel, cobalt, chromium, molybdenum, tantalum and the Lanthanide series, and their alloys or intermetallics.
3. The anode of claim of claim 2, wherein the passivable metal substrate is nickel-plated copper.
4. The anode of claim 1, wherein the coating comprises
20 at least one electrically conductive and electrochemically active constituent.
5. The anode of claim 1, wherein the coating further comprises at least one electrocatalyst or a precursor thereof for the formation of oxygen gas.
- 25 6. The anode of claim 1, wherein the coating further comprises a bonding material substantially resistant to cryolite for bonding the constituents of the coating together and onto the passivable metal substrate.
7. The anode of claim 1, wherein the coating is
30 obtainable by applying its constituents in the form of powder onto the passivable metal substrate.

- 14 -

8. The anode of claim 1, wherein the coating is obtainable from a slurry or a suspension containing colloidal or polymeric material.

9. The anode of claim 8, wherein the slurry or
5 suspension contains at least of alumina, ceria, lithia, magnesia, silica, thoria, yttria, zirconia, tin oxide and zinc oxide, and colloids containing active constituents of the coating or precursors thereof, all in the form of colloids or polymers.

10. The anode of claim 6, wherein the or at least one of
10 said electrochemically active constituent(s) is selected from the group consisting of oxides, oxyfluorides, phosphides, carbides and combinations thereof.

11. The anode of claim 10, wherein said oxides comprise
15 spinels and/or perovskites.

12. The anode of claim 11, wherein said spinels are doped, non-stoichiometric and/or partially substituted spinels, the doped spinels comprising dopants selected from the group consisting of Ti^{4+} , Zr^{4+} , Sn^{4+} , Fe^{4+} , Hf^{4+} ,
20 Mn^{4+} , Fe^{3+} , Ni^{3+} , Co^{3+} , Mn^{3+} , Al^{3+} , Cr^{3+} , Fe^{2+} , Ni^{2+} , Co^{2+} , Mg^{2+} , Mn^{2+} , Cu^{2+} , Zn^{2+} and Li^{+} .

13. The anode of claim 12, wherein said spinels comprise a ferrite and/or a chromite.

14. The anode of claim 13, wherein said ferrite is
25 selected from the group consisting of cobalt, manganese, molybdenum, nickel and zinc, and mixtures thereof.

15. The anode of claim 14, wherein the ferrite is doped with at least one oxide selected from the group consisting of chromium, titanium, tantalum, tin, zinc and
30 zirconium oxide.

- 15 -

16. The anode of claim 14, wherein said ferrite is nickel-ferrite or nickel-ferrite partially substituted with Fe^{2+} .
17. The anode of claim 13, wherein said chromite is
5 selected from the group consisting of iron, cobalt, copper, manganese, beryllium, calcium, strontium, barium, magnesium, nickel and zinc chromite.
18. The anode of claim 10, wherein the or at least one of said electrochemically active constituent(s) comprises
10 at least one Lanthanide as an oxide or an oxyfluoride, and mixtures thereof.
19. The anode of claim 18, wherein said oxyfluoride is cerium oxyfluoride.
20. The anode of claim 4, wherein the or at least one of
15 said electrochemically active constituent(s) comprises at least one metal selected from iron, chromium, copper and nickel, and oxides, mixtures and compounds thereof.
21. The anode of claim 5, wherein said electrocatalyst(s) is/are selected from iridium,
20 palladium, platinum, rhodium, ruthenium, silicon, tin and zinc, the Lanthanide series and mischmetal, and their oxides, mixtures and compounds thereof.
22. The anode of claim 1, wherein the coating is obtainable from a precursor, the constituents of which
25 react among themselves to form the coating favoured by heat-treatment.
23. The anode of claim 1, wherein the coating is obtainable from a precursor, at least one constituent of which reacts with the passivable metal substrate to
30 form the coating favoured by heat-treatment.
24. The anode of claim 1, wherein the passivable metal substrate is coated on an electronically conductive core.

- 16 -

25 The anode of claim 24, wherein the core is selected from metals, alloys, intermetallics, cermets and conductive ceramics.

26 The anode of claim 25, wherein the metals of the
5 core are selected from copper, chromium, cobalt, iron, aluminium, hafnium, molybdenum, nickel, niobium, silicon, tantalum, titanium, tungsten, vanadium, yttrium and zirconium, and combinations and compounds thereof.

27. The anode of claim 26, wherein the core is an alloy
10 comprising 10 to 30 weight% of chromium, 55 to 90 weight% of at least one of nickel, cobalt and/or iron and 0 to 15 weight% of at least one of aluminium, hafnium, molybdenum, niobium, silicon, tantalum, tungsten, vanadium, yttrium and zirconium.

15 28. The anode of claim 24, wherein the core is covered with an oxygen barrier layer.

29. The anode of claim 28, wherein the oxygen barrier layer comprises chromium oxide.

20 30. The anode of claim 28, wherein the oxygen barrier layer comprises black non-stoichiometric nickel oxide.

31. The anode of claim 28, wherein the oxygen barrier layer is covered with at least one protective layer consisting of copper or copper and at least one of nickel and cobalt, and/or oxides thereof to protect the oxygen
25 barrier layer by inhibiting its dissolution into the electrolyte.

32. A method of manufacturing a non-carbon metal-based anode of a cell for the electrowinning of aluminium, in particular by the electrolysis of alumina dissolved in
30 fluoride-containing electrolyte, said method comprising coating a substrate of electrically conductive metal resistant to high temperature and the surface of which becomes passive and substantially inert to the

- 17 -

electrolyte with at least one layer of an electrochemically active coating precursor, and heat-treating the or each layer on the substrate to obtain a coating adherent to the passivable metal substrate making the surface of the anode electrochemically active for the oxidation of oxygen ions present at the electrolyte interface.

33. The method of claim 32, wherein the passivable metal substrate comprises at least one metal selected from nickel, cobalt, chromium, molybdenum, tantalum and the Lanthanide series, and their alloys or intermetallics.

34. The method of claim of claim 33, wherein the passivable metal substrate is nickel-plated copper.

35. The method of claim 32, wherein the coating is formed by applying at least one electrically conductive and electrochemically active constituent or a precursor thereof onto the passivable metal substrate and heat treating.

36. The method of claim 32, wherein the coating is formed by further applying at least one electrocatalyst or a precursor thereof for the formation of oxygen gas.

37. The method of claim 32, wherein the coating is formed by further applying a bonding material substantially resistant to cryolite for bonding the constituents of the coating together and onto the passivable metal substrate.

38. The method of claim 32, wherein the coating is obtained by applying its constituents in the form of powder onto the passivable metal substrate.

39. The method of claim 32, wherein the coating is obtained from a slurry or suspension containing colloidal or polymeric material.

- 18 -

40. The method of claim 39, wherein the slurry or suspension contains at least one of alumina, ceria, lithia, magnesia, silica, thoria, yttria, zirconia, tin oxide and zinc oxide, and colloids containing active constituents of the coating or precursors thereof, all in the form of colloids or polymers.
41. The method of claim 35, wherein the or at least one of said electrochemically active constituent(s) is selected from the group consisting of oxides, oxyfluorides, phosphides, carbides and combinations thereof.
42. The method of claim 41, wherein said oxides comprise spinels and/or perovskites.
43. The method of claim 42, wherein said spinels are doped, non-stoichiometric and/or partially substituted spinels, the doped spinels comprising dopants selected from the group consisting of Ti^{4+} , Zr^{4+} , Sn^{4+} , Fe^{4+} , Hf^{4+} , Mn^{4+} , Fe^{3+} , Ni^{3+} , Co^{3+} , Mn^{3+} , Al^{3+} , Cr^{3+} , Fe^{2+} , Ni^{2+} , Co^{2+} , Mg^{2+} , Mn^{2+} , Cu^{2+} , Zn^{2+} and Li^{+} .
44. The method of claim 42, wherein said spinels comprise a ferrite and/or a chromite.
45. The method of claim 44, wherein said ferrite is selected from the group consisting of cobalt, manganese, molybdenum, nickel and zinc, and mixtures thereof.
46. The method of claim 45, wherein the ferrite is doped with at least one oxide selected from the group consisting of chromium, titanium, tantalum, tin, zinc and zirconium oxide.
47. The method of claim 45, wherein said ferrite is nickel-ferrite or nickel-ferrite partially substituted with Fe^{2+} .

- 19 -

48. The method of claim 44, wherein said chromite is selected from the group consisting of iron, cobalt, copper, manganese, beryllium, calcium, strontium, barium, magnesium, nickel and zinc chromite.

5 49. The method of claim 41, wherein the or at least one of said electrochemically active constituent(s) comprises at least one Lanthanide as an oxide or a oxyfluoride , and mixtures thereof.

10 50. The method of claim 49, wherein said oxyfluoride is cerium oxyfluoride.

51. The method of claim 35, wherein the or at least one of said electrochemically active constituent(s) comprises at least one metal selected from iron, chromium, copper and nickel, and oxides, mixtures and compounds thereof.

15 52. The anode of claim 36, wherein said electrocatalyst(s) is/are selected from iridium, palladium, platinum, rhodium, ruthenium, silicon, tin and zinc, the Lanthanide series and mischmetal, and their oxides, mixtures and compounds thereof.

20 53. The method of claim 32, comprising reacting the constituents of a precursor of the coating among themselves to form the coating.

25 54. The method of claim 32, comprising reacting at least one constituent of a precursor of the coating with the passivable metal substrate to form the coating.

30 55. The method of claim 41, wherein at least one constituent of the coating is applied onto the substrate by plasma spraying, physical vapour deposition, chemical vapour deposition, electrodeposition or callendering rollers.

- 20 -

56. The method of claim 32, wherein at least one of the constituent of the coating is applied onto the substrate by rollers, brush or spraying.

57. The method of claim 32, comprising coating the
5 passivable metal substrate onto an electronically conductive core.

58. The method of claim 57, wherein the core is selected from metals, alloys, intermetallics, cermets and conductive ceramics.

10 59. The method of claim 57, wherein the metals of the core are selected from copper, chromium, cobalt, iron, aluminium, hafnium, molybdenum, nickel, niobium, silicon, tantalum, titanium, tungsten, vanadium, yttrium and zirconium, and combinations and compounds thereof.

15 60. The method of claim 59, wherein the core is an alloy comprising 10 to 30 weight% of chromium, 55 to 90 weight% of at least one of nickel, cobalt and/or iron and 0 to 15 weight% of at least one of aluminium, hafnium, molybdenum, niobium, silicon, tantalum, tungsten,
20 vanadium, yttrium and zirconium.

61. The method of claim 57, comprising forming an oxygen barrier layer on the core.

62. The method of claim 61, comprising oxidising the surface of the core to form the oxygen barrier layer.

25 63. The method of claim 61, comprising applying a precursor of the oxygen barrier layer onto the core and heat treating.

64. The method of claim 61, wherein the oxygen barrier layer comprises chromium oxide.

30 65. The method of claim 61, wherein the oxygen barrier layer comprises black non-stoichiometric nickel oxide.

- 21 -

66. The method of claim 61, comprising covering the oxygen barrier layer with at least one protective layer consisting of copper or copper and at least one of nickel and cobalt, and/or oxides thereof to protect the oxygen
5 barrier layer by inhibiting its dissolution into the electrolyte.

67. The method of claim 32 for reconditioning a non-carbon metal-based anode according to claim 1, when at least part of the active coating has become non-active or
10 worn out, said method comprising clearing the surface of the substrate before re-coating said surface with a coating adherent to the passivable metal substrate to re-make the surface of the anode electrochemically active for the oxidation of oxygen ions.

68. A cell for the production of aluminium by the electrolysis of alumina dissolved in a fluoride-containing electrolyte having at least one non-carbon metal-based anode comprising an electrically conductive passivable metal substrate and a conductive coating
15 20 having an electrochemically active surface according to claim 1.

69. The cell of claim 68, wherein the electrolyte is cryolite.

70. The cell of claim 68, comprising at least one
25 aluminium-wettable cathode.

71. The cell of claim 70, which is in a drained configuration, comprising at least one drained cathode on which aluminium is produced and from which aluminium continuously drains.

72. The cell of claim 68, which is in a bipolar configuration and wherein the anodes form the anodic side of at least one bipolar electrode and/or a terminal anode.
30

- 22 -

73. The cell of claim 68, comprising means to circulate the electrolyte between the anodes and facing cathodes and/or means to facilitate dissolution of alumina in the electrolyte.

5 74. The cell of claim 68, wherein during operation the electrolyte is at a temperature of 750°C to 970°C.

75. Use of the anode of claim 1 for the production of aluminium in a cell for the electrowinning of aluminium by the electrolysis of alumina dissolved in a fluoride-
10 containing electrolyte, wherein oxygen ions in the electrolyte are oxidised and released as molecular oxygen by the electrochemically active anode coating.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/IB 99/00084

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 C25C3/12 C25C7/02

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C25C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 4 541 912 A (D. R. SECRIST) 17 September 1985 see column 6; claims 1-6	1, 2, 4, 7
X	EP 0 306 101 A (ELTECH SYSTEMS CORPORATION) 8 March 1989 cited in the application	1, 2, 4-6, 10-14, 18-21
Y	see whole document	8, 9, 22, 32, 33, 35-37, 39-45, 49-53, 55, 56, 68, 69, 74, 75

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

10 May 1999

Date of mailing of the international search report

19/05/1999

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Groseiller, P

INTERNATIONAL SEARCH REPORT

International Application No

PCT/IB 99/00084

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	<p>WO 93 20026 A (MOLTECH INVENT SA) 14 October 1993</p> <p>see page 3, line 35 - page 4, line 2 see page 6, line 10 - line 30 see page 8, line 4 - line 5 see page 12, line 3 - line 12 see page 13, line 16 -----</p>	<p>8, 9, 22, 32, 33, 35-37, 39-45, 49-53, 55, 56, 68, 69, 74, 75</p>

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/IB 99/00084

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 4541912 A	17-09-1985	NONE	
EP 306101 A	08-03-1989	AT 81160 T	15-10-1992
		AT 87671 T	15-04-1993
		AU 2320088 A	31-03-1989
		AU 614995 B	19-09-1991
		AU 2327688 A	31-03-1989
		AU 615002 B	19-09-1991
		AU 2424388 A	31-03-1989
		AU 2428988 A	31-03-1989
		CA 1328243 A	05-04-1994
		CA 1306147 A	11-08-1992
		CA 1306148 A	11-08-1992
		CN 1042737 A	06-06-1990
		DD 283655 A	17-10-1990
		DE 3875040 A	05-11-1992
		DE 3879819 A	06-05-1993
		WO 8901991 A	09-03-1989
		WO 8901992 A	09-03-1989
		WO 8901993 A	09-03-1989
		WO 8901994 A	09-03-1989
		EP 0306099 A	08-03-1989
		EP 0306100 A	08-03-1989
		EP 0306102 A	08-03-1989
		ES 2052688 T	16-07-1994
		NO 177107 B	10-04-1995
		NO 302904 B	04-05-1998
		US 5069771 A	03-12-1991
		US 4956068 A	11-09-1990
		US 4960494 A	02-10-1990
WO 9320026 A	14-10-1993	US 5310476 A	10-05-1994
		US 5364513 A	15-11-1994
		AU 677777 B	08-05-1997
		AU 3950993 A	08-11-1993
		AU 3951093 A	08-11-1993
		CA 2131287 A	14-10-1993
		CA 2131288 A,C	14-10-1993
		DE 69319721 D	20-08-1998
		DE 69319721 T	25-03-1999
		WO 9320027 A	14-10-1993
		EP 0633870 A	18-01-1995
		EP 0633871 A	18-01-1995
		NO 943656 A	30-09-1994
		NO 943657 A	30-09-1994
		WO 9325731 A	23-12-1993
		US 5340448 A	23-08-1994
		US 5527442 A	18-06-1996
		AU 664475 B	16-11-1995
		AU 4525393 A	04-01-1994
		BR 9306538 A	15-09-1998
		CA 2137816 A	23-12-1993
		EP 0663022 A	19-07-1995
		EP 0892085 A	20-01-1999
		HU 72817 A	28-05-1996
		NO 944750 A	08-12-1994
		US 5534119 A	09-07-1996